
# WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



INTERNATIONAL APPLICATION PUBLIS	HED I	UNDER THE PATENT COOPERATION TREATY (PCT)
(51) International Patent Classification 6:	4.1	(11) International Publication Number: WO 99/30147
G01N 30/48, 30/60, 30/56	A1	(43) International Publication Date: 17 June 1999 (17.06.99).
(21) International Application Number: PCT/US (22) International Filing Date: 8 December 1998 (		CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC
(30) Priority Data: 08/987,287 9 December 1997 (09.12.97)	) U	Published  With international search report.
(71) Applicant: THE BOARD OF TRUSTEES OF THE L STANFORD JUNIOR UNIVERSITY [US/US]; St 900 Welch Road, Palo Alto, CA 94304 (US).	ELAN uite 350	D, O,
(72) Inventors: ZARE, Richard, N.; 724 Santa Ynez, Stant 94305 (US). DULAY, Maria, T.; 955-E La Mesa Sunnyvale, CA 92354 (US). KULKARNI, Rajan, P Butterfield Street, Loma Linda, CA 92354 (US).	Тегтас	e.
(74) Agents: HSUE, James, S. et al.; Majestic, Parsons, & Hsue P.C., Suite 1100, Four Embarcadero Cen Francisco, CA 94111-4106 (US).	Sieber ter, Sa	nt n

(54) Title: SEPARATION COLUMN CONTAINING POROUS MATRIX AND METHOD OF PACKING COLUMN



### (57) Abstract

A mixture of chromatographic particles and a solution of water, alcohol and metal alkoxide may be injected by means of a syringe into a capillary column as a gel. The volatile components in the gel are evaporated by means of heating and gas pressure reduction to form a porous sol-gel glass matrix attached to the inner wall of the separation channel. The pores are large enough for the passage of protons, neutral and ionic species but are too small to permit significant leaching of the chromatographic particles. The separation column so formed requires no frits to maintain the glass matrix in place in the column. Electrical potential difference and/or pressure difference may be applied to cause fluid flow in the separation column to cause electrophoretic and chromatographic separation.

# FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad .
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
СН	Switzerland	KG	Kyrgyzstan	NO	Norway	zw	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal ·		
CU	Cuba	KZ	Kazakstan	RO	Romania		
cz	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	u	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

DISCOURS AND DODGE 4784 I

10

15

20

25

1

# SEPARATION COLUMN CONTAINING POROUS MATRIX AND METHOD OF PACKING COLUMN

#### BACKGROUND OF THE INVENTION

invention relates to a separation system employing a column containing a porous matrix embedded with chromatographic particles and a method of packing a channel with the matrix to make the column.

Capillary zone electrophoresis (CZE), with its high peak capacity (i.e., the number of peaks separated per unit time), has long been proven to be an attractive analytical technique for separating ionic species by their electrophoretic mobilities. The separation of neutral species via CZE, however, has remained more problematic. To improve the separation of neutral species via capillary electrophoresis, the technique of capillary electrochromatography (CEC) has been employed, which is a promising technique that seeks to combine the advantages of capillary electrophoresis chromatography as described in the article by M.T. Dulay et al. in Chromatogr. A., 725 (1996) pp. 361-365).

In CEC, the separation of uncharged analytes is based on partitioning of chromatographic particles such as octadecylsilica, while the separations of charged analytes are based both partitioning and electrophoretic mobility. Existing techniques for the preparation of packed capillary columns are based on either a slurry packing method or an electrokinetic packing method of small-bore capillary columns. electrokinetic packing method may be more advantageous

WO 99/30147 PCT/US98/26004

2

packed capillary columns with micron-sized inner diameters. Disadvantages of the electrokinetic packing method include the limited choices of chromatographic phases (i.e., only charged particles can be used) and the need for both inlet and outlet frits to prevent the chromatographic particles from leaving the capillary column. This causes the columns to be difficult and time consuming to make.

It is therefore desirable to provide a separation column with improved characteristics and that are easy to make.

#### SUMMARY OF THE INVENTION

5

10

15

20

25

30

One aspect of the invention is directed towards a separation column comprising a separation channel having a channel wall and a separation medium in the channel. The medium includes a porous matrix attached to the channel wall and chromatographic particles embedded in the matrix forming a packed channel. The channel has no frit therein adjacent to the separation medium.

Another aspect of the invention is directed towards an apparatus for separating a sample into its components, comprising a separation channel having a channel wall; a separation medium in the channel, and means for causing a fluid containing a sample present in a channel to flow and the sample to separate. The medium includes a porous matrix attached to the channel wall and chromatographic particles embedded in the matrix, forming a packed channel. The channel has no frit therein adjacent to the separation medium.

One more aspect of the invention is directed towards a method for making a separation column, comprising introducing a mixture of chromatographic particles and a solution of a monomer and a crosslinking reagent into a separation channel, such channel

10

15

20

25

30

3

having a wall; and causing the mixture to form a porous matrix attached to the channel wall with said particles embedded therein.

# BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a partially cross-sectional and partially schematic view of a section of a separation column along a longitudinal axis of the column and of a needle portion of a syringe for injecting a mixture of chromatographic particles and a solution of water, alcohol and a metal alkoxide into the column to illustrate a preferred embodiment of the invention.

Fig. 2 is a cross-sectional view of a portion of the column of Fig. 1 along a longitudinal axis of the column, where the volatile components in the mixture injected into the column have been removed to form a porous sol-gel with chromatographic particles embedded therein to illustrate the invention.

Figs. 3A and 3B are cross-sectional views of the separation column shown in Fig. 2 along the line 3A, 3B - 3A, 3B in Fig. 2 to illustrate two different embodiments of the separation column.

Fig. 4 is a partially schematic and partially cross-sectional view of a separation system employing the separation column of Fig. 2 to illustrate a preferred embodiment of the invention.

Fig. 5 is a schematic view of a system for making the separation column of Fig. 2.

Fig. 6 is a cross-sectional view of a portion of a separation column along a longitudinal axis of the column to illustrate another embodiment of the column and an alternative method for packing the column.

For simplicity in description, identical components are labeled by the same numerals in this application.

### DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

WO 99/30147 PCT/US98/26004

4

In the preferred embodiment, this invention employs a metal alkoxide sol-gel process. The metal alkoxide sol-gel process is a method of preparing metal oxide glasses by hydrolyzing a solution of water, alcohol, and a metal alkoxide source. The sources of these metal oxides, or silanes, are the alkoxy compounds of type R<sub>n</sub>Si(OR')<sub>4-n</sub> as described by C.J. Brinker et al. in Sol-Gel Science, Academic Press, Inc., New York, NY, 1990. commonly used The most of these compounds (TEOS, tetraethylorthosilicate  $Si(OC_2H_5)_4)$ , other compounds such as titanates, and zirconates may also be used for this invention. As these substances polymerize, gelation of the solution occurs. If the volatile solvents in the wet gel are allowed to evaporate, the gel shrinks and hardens, creating a hard porous glass.

Since sol-gel glasses are formed from solution, other molecules can be embedded inside the pores or inside the cavities created. When the solvent evaporates from the gel, the glass that is created is porous. The porosity of the glass allows for the diffusion of protons (and other neutral or ionic species) through the channels. These pores, however, must be large enough to allow species diffusion, but small enough that significant amounts of chromatographic materials cannot leave the xerogel matrix.

Fig. 1 is a partially cross-sectional and partially schematic view of a portion of a separation column 12 along a longitudinal axis of the column and a needle portion 11 of a syringe (not shown) injecting a mixture 13 of chromatographic particles and a solution to illustrate the preferred embodiment of the invention. As shown in Fig. 1, a needle portion 11 is used to inject into a channel within a tube 12, a mixture 13 of chromatographic particles in a solution of water, alcohol and a metal alkoxide. This mixture forms a wet

5

10

15

20

25

30

gel 13 in tube 12. After the volatile solvents in the wet gel 13 have evaporated, the gel 13 shrinks and hardens, creating a hard porous glass 13' shown in Fig. 2.

Fig. 2 is a cross-sectional view of column 12 along 5 a longitudinal axis of the column and the hard porous glass 13' in the column resulting from evaporation of the volatile solvents in the wet gel 13 of Fig. 1. shown in Fig. 2, glass 13' includes pores 4 and chromatographic particles 6 embedded therein. As noted 10 above, the porosity of the glass 13' allows for the diffusion of protons and other neutral or ionic species, but small enough that significant amounts chromatographic particles 6 cannot leave the glass 15 matrix 13'. Glass 13' forms a secure bond to the inner wall of the tube 12, so that no frit is required adjacent to the glass 13' to maintain the matrix glass 13' in place in tube 12. While pores 4 are big enough to allow diffusion of protons, neutral and ionic 20 species, they are too small for most of the chromatographic particles 6. This prevents leaching of the particles when a fluid is passed through the glass matrix. Thus, when a sample is carried by fluid through glass 13!, the sample components will interact with the 25 chromatographic particles 6 and become partitioned or separated.

Tube 12 can have many different cross-sections, such as a circular cross-section shown in Fig. 3A, the cross-section being normal to a longitudinal axis of the tube, shown as tube 12'. Alternatively, tube 12 can have an elongated cross-section as shown in Fig. 3B, where the tube is formed by two flat plates 12" where the tube is formed by sealing the adjacent edges of the two plates by means of an adhesive 15. Such and other cross-sections are possible for tube 12 and are within the scope of the invention. In some embodiments, the

30

internal dimension of tube or channel 12 may range from about 5 to about 3,000 microns. Where tube 12 is a capillary, its internal dimension may range from about 5 to about 300 microns.

Chromatographic particles 6 may comprise uniformly sized particles of the same type, or a mixture of different types of particles of different sizes. Preferably, the particles are of dimensions greater than 0.2 microns.

Fig. 4 is a partially schematic and partially cross-sectional view of a separation system employing a column 12 to illustrate the preferred embodiment of the invention. As shown in Fig. 4, the inlet end 12a of the column is immersed in an electrolyte buffer 14 contained in a reservoir 16. The outlet end 12b is immersed in an electrolyte buffer in reservoir 18. An electrical potential of several kilovolts is applied by high 20 through electrodes 30 voltage source electrolyte buffer 14 in input and output reservoirs 16, 18, causing a potential difference and electric field along the column 12. Such potential difference causes an electroosmotic flow in tube 12 from reservoir 16 towards reservoir 18. A sample may be introduced into inlet 12a by means known to those skilled in the art, such as by gravity or by electrokinetic injection. sample would be caused to separate in tube 12 due to electrophoresis. In addition, the interaction between the sample components (which may be uncharged or neutral electrically) and the chromatographic particles 6 in the glass matrix 13' causes chromatographic separation of the components as well.

Instead of, or in addition to, the use of electrical potential to cause fluid flow in column 12, the fluid flow can also be caused by applying a pressure differential along the column 12, which, in addition to or instead of the electric field applied along the

5

10

15

20

25

30

column, causes fluid flow from reservoir 16 to reservoir This can be performed by using an enclosed reservoir 16 except for an inlet 16a, through which gas pressure is applied as shown in Fig. 4. pressure may be supplied by means of a pump (not shown) 5 for example. The gas pressure applied through inlet 16a causes buffer 14 to be pushed downward and the buffer to flow into the inlet 12a and column 12 to reservoir 18. Instead of using a pump to apply a pressure differential in column 12, a pressure differential may also be 10 applied by raising the column inlet 12a to a position 12a' at an elevation higher than the outlet end 12b of the column, as shown in dotted lines in Fig. 4. as shown in dotted lines, the new positions of the inlet 12a' of the column, of reservoir 16' containing buffer 15 and electrode 30' immersed in the buffer in reservoir 16' are all at elevations above the outlet end 12b of the column. Alternatively, instead of raising the inlet end 12a, the same goal can be achieved by 20 lowering outlet end 12b of the tube, by lowering reservoir 18, electrode 30 in such reservoir and end 12b. Or, the pressure in reservoir 18 can be reduced by means of a pump (not shown) to one below that of reservoir 16 to achieve a pressure differential between 25 ends 12a, 12b, and to create fluid flow in tube 12.

In the embodiment of Fig. 2, only a portion of the column 12 is filled with the porous glass with chromatographic particles embedded therein, and the remaining portion of the column is not filled with the porous glass. In an arrangement similar to that in prior detection schemes, the separated sample components may be detected optically, such as by laser induced fluorescence as described in U.S. Patent No. 4,675,300 in a transparent column portion 12t that is transparent to radiation and downstream from glass 13' as shown in Figs. 2 and 4. As shown in Fig. 2, the portion 12t does

30

WO 99/30147 PCT/US98/26004

5

10

15

20

25

30

35

8

not contain any of the chromatographic particles present in glass matrix 13' and transmits radiation without significant scattering, such as UV or visible light. The sample components passing through such portion 12t may be illuminated by means of radiation along arrow 50 to induce fluorescence, where the induced fluorescence may be detected by means of a detector 17 preferably placed away from the path of radiation 50. This is shown schematically in Fig. 4, where a detector 100 detects the separated sample components at location 12c. When detector 100 detects the sample components by means of laser induced fluorescence, the sample components may need to be first tagged by means of a fluorophore and detector 100 includes a laser source as well as a photodetector.

In order to facilitate the evaporation of the volatile solvents in mixture 13 in Fig. 1, the tube 12 containing mixture 13 may be placed in an oven chamber 150 as shown in Fig. 5. Tube 12 is supported by a pedestal 152 in the oven chamber and heat is applied by a heating coil 154 through which a current is passed by means of a power supply 156. To further facilitate the evaporation of volatile solvents, the gas pressure in oven chamber 150 is reduced by means of a pump 160. While both heating and reduction of gas pressure may be used together to accelerate the evaporation of volatile solvents, heating may be used without pressure reduction and vice versa; all such variations are within the scope When the volatile solvents have of the invention. evaporated, mixture 13 then forms a porous sol-gel glass that is attached securely to the inner walls of tube 12, with the chromatographic particles 6 embedded therein. It has been found that in some instances, a hardened porous sol-gel glass may form in about 24 hours.

To achieve a more uniform distribution of the chromatographic particles in the sol-gel, it may be

15

20

25

30

35

9

desirable to agitate the mixture 13 when the volatile components are escaping from the mixture. This can be done for example by rotating the tube along arrows 158, shaking the tube along arrows 162, or supplying ultrasonic pulses along arrows 164 from an ultrasonic source (not shown) as shown in Fig. 5 in a manner known to those skilled in the art.

With this monolithic packing method, chromatographic materials that are charged and uncharged in nature can be embedded into the sol-gel matrix. Different functionalized/derivatized sol-gel precursors can be used to prepare sol-gel glasses with different physical properties, such as pore size and surface The pore size may be selected by choosing an charge. appropriate sol-gel precursor. For example, to obtain larger pores, tetramethylorthosilicate may be used as precursor the instead of tetraethylorthosilicate indicated above.

Mixture 13 may be prepared as follows. Micron or submicron sized chromatographic particles, such as octadecylsilica may be added to a solution of water, alcohol, acid (optional) or base (optional) and a metal oxide source. The metal oxide source may include a silicate, titanate or zirconate. The resulting solution or mixture 13 formed is injected by syringe into a column and heated overnight. No pre-fabricated frits is required.

Instead of using a syringe to inject the mixture 13 into a channel as described above in reference to Fig. 1, the mixture 13 may be introduced by means of a pressure differential as illustrated in Fig. 6, which is a cross-sectional view of a tube 12 along a longitudinal axis. As shown in Fig. 6, a pressure differential is applied between the inlet end 12a and outlet end 12b, such as by means of a pump (not shown), in order to introduce a mixture 53 of water, alcohol, acid

(optional) or base (optional) and a metal oxide source, without chromatographic particles embedded therein, followed by a mixture 13 of chromatographic particles with a solution such as solution 53, which is again followed by solution 53 to fill tube 12. and mixture 13 are then treated in the manner described above in reference to Fig. 5 to remove the volatile components and to form a porous sol-gel throughout the column 12. Only the section 12d of the tube containing the porous sol-qel glass with chromatographic particles embedded therein is used for chromatographic separation. The remaining sections of the tube next to section 12d porous sol-gel glass contain containing chromatographic particles and, therefore, do not scatter light used for detection, so that the scheme illustrated in Fig. 4 above may be used for detecting separated sample components in a similar manner employing the column of Fig. 6 that has been filled by a porous glass. The column 150 of Fig. 6 is advantageous in that the entire tube is filled by the porous sol-gel glass so that there will no significant pressure differential between the fluid in the porous glass in section 12d and that in the porous glass in the remaining sections of This enhances separation performance. the tube.

The pressure differential between the inlet and outlet ends 12a, 12b may be created in many ways, such as by pushing (i.e. by increasing pressure) the mixtures 53, 13 into the inlet end 12a, or by reducing the gas pressure at outlet end 12b to draw in solution 53 and mixture 13 as described (since such solution and mixture are under the higher atmospheric pressure at end 12a), by means of a pump (not shown). The inlet end 12a may also be placed at a higher elevation compared to outlet end 12b so that solution 53 and mixture 13 may be introduced by hydrostatic pressure differential.

5

10

15

20

25

30

10

15

The packed "fritless" column columns 12 will facilitate the analysis of complex mixtures that may contain charged and/or uncharged compounds. The separation of a mixture of uncharged organic compounds has been demonstrated using a column packed in this manner. Advantages of the disclosed method include (i) easy and rapid injection of the hydrolysis reaction solution into the column, (ii) the elimination of inlet and outlet frit fabrication, (iii) incorporation of charged or uncharged chromatographic materials in the sol-gel matrix, (iv) UV transparency of the sol-gel glass, (v) potential for automation of many samples, and (vi) potential for large-scale preparative use. results in a total column preparation approximately 24 hours and avoids the use of high pressures for post-column conditioning. The use of high voltages is also avoided during column preparation. This system is superior to both the electrokinetic and slurry packing methods.

20 Instead of using a sol-gel process as described above, other types of polymerization processes may be used, such as that described in the article "Macroporous Polyacrylamide/Poly(ethylene glycol) Matrixes Stationary Phrases in Capillary Electrochromatography, " by Anders Palm and Milos V. Novotny, Analytical 25 Chemistry, Vol. 69, No. 22, November 15, 1997, pp. 4499-4507; or the articles by P.G. Righetti, B.C.W. Brost and R.S. Snyder, in J. Biochem. Biophys. Methods, 1981, No. 4, pp. 347-363, and by P.G. Righetti, S. Caglio, S. Saracchi and M. Quaroni in Electrophoresis, 1992, No. 30 13, pp. 587-595. As described in these three articles, a porous matrix may be formed by polymerizing a solution of a monomer and a cross-linking reagent or initiator. If said solution is mixed with chromatographic particles and such mixture is used instead of mixture 13 to form 35 porous matrix with chromatographic particles

10

15

20

25

30

35

embedded therein, such matrix may also be used in a separation column for separating a sample into its components in the manner described above. When such a mixture is polymerized, the matrix forms a secure bond to the inner wall of the separation channel so that no frit is necessary to keep the matrix in place. pores formed are big enough to permit diffusion species but small enough to prevent significant leaching of the chromatographic particles trapped therein. The porous matrix without the particles is transparent to radiation so that the configuration of Fig. 6 described above may be used, where the entire tube is filled with the porous matrix but only a section of the matrix is embedded with the In this chromatographic particles. manner, separated components may be detected downstream from the particles by a detector in a known manner, such as by means of laser induced fluorescence detection. above-described method for introducing the mixture 13 may also be used for introducing a mixture of the particles with other types of monomers and cross-linking reagents (optional), such as acrylamide or ethylene glycol and an optional base or acid acting crosslinking reagnet.

A porous matrix (whether or not embedded with particles) may be formed by heating or supplying radiation to a solution of a monomer such as acrylamide or ethyleneglycol and a cross-linking reagent (optional) base or acid to form a macroporous polyacrylamide or poly(ethylene glycol) matrix. The thermally is achieved polymerization In reference to the article by Palm and photochemistry. Novotny, since chromatographic particles are used in this invention for sample separation, there is no need in this invention to include alkyl ligands as described in the Palm and Novotny article. Polymerization techniques different from the above may also be used for

forming the porous matrix; such and other variations are within the scope of the invention.

While the invention has been described above by reference to various embodiments, it will be understood that different changes and modifications may be made without departing from the scope of the invention, which is to be defined only by the appended claims and the equivalents thereof.

BNSDOCID: <WO\_\_9830147A1\_l\_>

# WHAT IS CLAIMED IS:

- 1. A separation column comprising:
  - a separation channel having a channel wall; and
- a separation medium in the channel, said medium including a porous matrix attached to the channel wall and chromatographic particles embedded in the matrix forming a packed channel, said channel having no frit therein.
- 2. The column of claim 1, said column having an internal dimension in the range of between 5 and 5,000 microns.
  - 3. The column of claim 1, said channel having a elongated cross-section.
- 4. The column of claim 1, said column having a first portion that is filled with said separation medium and a second portion adjacent to said first portion that transmits radiation.
  - 5. The column of claim 4, said second portion does not contain said separation medium.
- 20 6. The column of claim 1, wherein said matrix has pores therein large enough for passage of neutral and charged species but too small for passage of the chromatographic particles.
- 7. The column of claim 1, said particles being larger than 0.2 micron in dimensions.
  - 8. The column of claim 1, said particles being a mixture of different types of particles of different sizes.

- 9. The column of claim 1, said matrix including a sol-gel glass.
- 10. The column of claim 9, wherein said glass includes a silicate, titanate or zirconate.
- 11. The column of claim 1, said column being filled with a porous matrix, said matrix having embedded therein chromatographic particles in only a section of the column.
- 12. The column of claim 1, said matrix including 10 a polyacrylamide or polyethylene glycol.
  - 13 An apparatus for separating a sample into its components, comprising:
    - a separation channel having a channel wall;
- a separation medium in the channel, said medium including a porous matrix attached to the channel wall and chromatographic particles embedded in the matrix, forming a packed channel, said channel having no frit therein; and
- means for causing a fluid containing a sample 20 present in the channel to flow and the sample to separate.
  - 14. The apparatus of claim 13, said channel being a capillary having an internal dimension in the range of between 5 and 300 microns.
- 25 15. The apparatus of claim 13, said channel having a first section that is filled with said separation medium and a second section adjacent to said first portion that transmits radiation.

10

15

25

- 16. The apparatus of claim 15, said second section does not contain said separation medium.
- 17. The apparatus of claim 16, said second section containing a porous matrix not embedded with chromatographic particles.
  - 18. The apparatus of claim 17, said channel filled with a porous matrix.
  - 19. The apparatus of claim 15, said causing means causing the sample to pass through the second section, said apparatus further comprising:

means for applying radiation to the sample in the second section; and

means for detecting radiation from the second section to detect components of the sample passing through the second section.

- 20. The apparatus of claim 13, said causing means applying an electric field along the channel, so that the sample separates by electrophoresis and chromatography.
- 21. The apparatus of claim 13, said causing means applying a pressure differential along the channel, so that the sample separates by chromatography.
  - 22. The apparatus of claim 13, said causing means applying both an electric field and a pressure differential along the channel, so that the sample separates by electrophoresis and chromatography.
    - 23. The apparatus of claim 13, wherein said matrix has pores therein large enough for passage of neutral

and charged species but too small for passage of the chromatographic particles.


- 24. The apparatus of claim 13, said particles being larger than 0.2 micron in dimensions.
- 5 25. The apparatus of claim 13, said matrix including a sol-gel glass.
  - 26. The apparatus of claim 25, wherein said glass includes a silicate, titanate or zirconate.
- 27. The apparatus of claim 13, said column being filled with a porous matrix, said matrix having embedded therein chromatographic particles in only a section of the column.
  - 28. The apparatus of claim 13, said matrix including a polyacrylamide or polyethylene glycol.
- 29. A method for making a separation column, comprising:


introducing a mixture of chromatographic particles and a solution of a monomer and a cross-linking reagent into a separation channel, said channel having a wall;

- causing the mixture to form a porous matrix attached to the channel wall with said particles embedded therein.
  - 30. The method of claim 29, said introducing employing a pressure differential.
- 25 31. The method of claim 30, wherein said employing uses a syringe.

- 32. The method of claim 29, said channel being a capillary, wherein said introducing injects said mixture into said capillary.
- 33. The method of claim 29, wherein said causing includes heating or supplying radiation to the mixture until it gels.
  - 34. The method of claim 29, wherein said causing includes reducing gas pressure in a chamber containing the mixture, to remove volatile components from the mixture.
    - 35. The method of claim 29, wherein said causing includes agitating the mixture so that the particles are more uniformly distributed in the matrix.
- 36. The method of claim 35, wherein said agitating includes rotating or vibrating the channel, or applying ultrasonic pulses to the channel.
  - 37. The method of claim 29, wherein said introducing introduces a solution of water, alcohol and a metal alkoxide into the channel.
- 20 38. The method of claim 29, wherein said introducing introduces a solution of a acrylamide or ethylene glycol and a base or acid into the channel.

1/3











FIG.\_3A





SUBSTITUTE SHEET (RULE 26)






FIG.\_6

SUBSTITUTE SHEET (RULE 26)

# INTERNATIONAL SEARCH REPORT

Inter onal Application No
PCT/US 98/26004

A. CLASSIF IPC 6	G01N30/48 G01N30/60 G01N30/	56	
A consuling to	International Patent Classification (IPC) or to both national classific	ation and IPC	
B. FIELDS			
Minimum do IPC 6	cumentation searched (classification system followed by classificat ${\tt G01N}$	ion symbols)	
Documentat	ion searched other than minimum documentation to the extent that	such documents are included in the fields se	arched
Electronic da	ata base consulted during the international search (name of data be	ase and, where practical, search terms used	
·		•	
C. DOCUM	ENTS CONSIDERED TO BE RELEVANT		Relevant to claim No.
Category °	Citation of document, with indication, where appropriate, of the re	elevant passages	Neigvani (o Gain) No.
P,X	M.T. DULAY ET AL.: "Preparation characterization of monolithic p		1,14
	capillary columns loaded with		
	chromatographic particles" ANALYTICAL CHEMISTRY.,		
	vol. 70, no. 23, 1 December 1998	, pages	·
	5103-5107, XP002096511 COLUMBUS US		
	see the whole document		
		-/	
	·		
		:	
X Furt	ther documents are listed in the continuation of box C.	X Patent family members are listed	in annex.
° Special co	ategories of cited documents :	"T" later document published after the inte or priority date and not in conflict with	emational filing date
"A" docum	nent defining the general state of the art which is not detect to be of particular relevance	cited to understand the principle or th	eory underlying the
	document but published on or after the international	"X" document of particular relevance; the cannot be considered novel or canno	t de considered to
" docum	ent which may throw doubts on priority claim(s) or n is cited to establish the publication date of another	involve an inventive step when the do	claimed invention
citatio	on or other special reason (as specified) nent referring to an oral disclosure, use, exhibition or	cannot be considered to involve an in document is combined with one or m ments, such combination being obvious	ore other such docu-
"P" docum	means nent published prior to the international filing date but	in the art.  "&" document member of the same patent	
	than the priority date claimed  actual completion of the international search	Date of mailing of the international se	
	12 March 1999	01/04/1999	
	mailing address of the ISA	Authorized officer	
	European Patent Office, P.B. 5818 Patentiaan 2 NL - 2280 HV Rijswijk		
	Tel. (+31-70) 340-2040, Tx. 31 651 epo ni, Fax: (+31-70) 340-3016	Zinngrebe, U	

# INTERNATIONAL SEARCH REPORT

Inte onal Application No
PCT/US 98/26004

		PC1/US 98/26004
	ation) DOCUMENTS CONSIDERED TO BE RELEVANT	
Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 135 627 A (SOANE DAVID S) 4 August 1992  see column 1, line 5-13 see column 3, line 12-24 see column 7, line 19-42 see column 8, line 5-19 see column 10, line 32-51 see column 11, line 1-9	1-3,6-8, 11-14, 29-33
A	EP 0 779 512 A (HEWLETT PACKARD CO) 18 June 1997 see abstract; figures 1,3	4,5,15, 16,19
A	EP 0 439 318 A (YISSUM RES DEV CO) 31 July 1991 see abstract see page 3, line 23-27 see page 3, line 36-41	6-11, 23-27
<b>A</b>	US 5 637 135 A (OTTENSTEIN DANIEL M ET AL) 10 June 1997 see abstract see column 4, line 40 - column 5, line 5; figures 2A,6A,6B	1
	US 5 308 495 A (AVNIR DAVID ET AL) 3 May 1994 see abstract	

# INTERNATIONAL SEARCH REPORT

.formation on patent family members

Inter onal Application No
PCT/US 98/26004

Patent docume cited in search re		Publication date	Patent family member(s)	Publication date
US 5135627	A	04-08-1992	AU 652790 B AU 8949691 A CA 2093916 A EP 0558565 A JP 6501419 T WO 9206773 A	08-09-1994 20-05-1992 16-04-1992 08-09-1993 17-02-1994 30-04-1992
EP 0779512	Α	18-06-1997	NONE	
EP 0439318	A	31-07-1991	IL 93134 A AT 166459 T DE 69129422 D DE 69129422 T JP 6122521 A US 5650311 A US 5300564 A US 5824526 A US 5292801 A US 5371018 A	20-11-1997 15-06-1998 25-06-1998 07-01-1999 06-05-1994 22-07-1997 05-04-1994 20-10-1998 08-03-1994 06-12-1994
US 5637135	5 A	10-06-1997	NONE	
US 5308495	5 A	03-05-1994	US 5371018 A US 5650311 A US 5824526 A US 5292801 A	06-12-1994 22-07-1997 20-10-1998 08-03-1994